

Edition 01.2011	Norm	Parameters	Norm requirements	Quick Step values
Dimensions panel overall thickness panels per pack m2 per pack		1-strip 3-strip	1-strip 3-strip	1820x145 mm 1820x190 mm 12,5 mm 6 1,5834 m ² 2,0748 m ²
Panel construction Surface layer Coreboard Backing layer Tongue and groove		PEFC, FSC or legally controlled sources PEFC, FSC or legally controlled sources lengthwise width	Spruce or Pine	2,5 mm HDF ^{QS Mastercore} 1,35 mm Uniclic Uniclic Multifit
Surface layer wood species origine finishing grading			Oak Europe	Matt lacquer Marquant
Installation floating glued to subfloor		on Quick-Step underlay Quick-Step MS polymere resin	cf installation instructions cf installation instructions	
CE	EN 14342: 2008-09	notified body	DAP-PL-1033.00	level 4
PEFC				PEFC label
Warranty		domestic use Uniclic connection commercial	conditions in each pack	25 years Lifetime on request
Finishing wear resistance Scratch resistance Stain resistance	UV-curing varnish SIS 923509 DIN 68861 EN 13442	falling sand S 33 anti-scratch Top Coat with nano-technology	all except blue ink blue ink	5 to 7 layers 800-1000 100-1050 class 5 class 3
General aspect of an installed flooring	EN 13489	lipping - differences in height difference in width cupping lengthwise cupping in width	≤ 0,20 mm ≤ 0,20 mm ≤ 0,1% ≤ 0,2%	≤ 0,15 mm ≤ 0,15 mm ≤ 0,1% ≤ 0,2%
Castor chairs		use soft castors Type W (EN 12529) and/or suitable office mat		
Slip resistance	CEN/TS 15676			USRV 50-52
Emission of Formaldehyde	EN 717-1			E1
PCP				below detection limit
Heat resistance	EN 12664			0,106 m ² .K/W
Underfloor heating			consult special installation instructions	
Reaction to fire	EN 14342	CWFT		D _{fl} -s1